

## Light Reflectance & Total Solar Absorption Values

Colour	Light Reflectance Values 1	Total Solar Absorption 2
<b>Smooth Finish</b>		
Castle Grey	6.7	93.8
Deep Olive	6.7	93.9
Evergreen	9.2	88.4
Graphite	6.7	93.6
Marseille Clay	20.3	69.3
Anvil	8.26	92.4
Morocco	31.6	70.6
Obsidian	4.6	95.5
Ocean Blue	9.8	91.3
Pearl Grey	26.8	78.6
Russet	8.6	87.4
Smoke Grey	9.1	92.3
Oilskin	11.7	89.3
Drover Grey	38.6	66.7
Chalk	65.5	42.2
Cypress	5.6	94.6
Grey Gum	47.6	58.5
Basalt	12.9	88.6
Tundra	66.9	39.3
<b>Textured Finish</b>		
Ashwood	16.2	84.9
Cedar	5.8	89.3
Charcoal	3.5	96.7
Teak	5.1	92.8
Onyx	9.9	89.3
Pepper	7.9	90.4
Terracotta	5.8	87.7
Midnight	2.2	95.0
Rainforest	4.4	95.4
<b>Duo-tone Textured Finish</b>		
Eclipse	3.5	96.7

**Table 1 Light Reflectance & Total Solar Absorption Values**

1. ASTM Reference C609-7. Instrument: Macbeth Color-Eye 7000A
2. ASTM Reference C1549 & E903-96. Instrument: Devices & Devices Reflectometer, Model SSR-ER